

DATASHEET

Taubmans Tradex Oil Enamel Semi Gloss

TAUBMANS

Product Code:
274800



Taubmans Tradex Oil Enamel Semi Gloss

Taubmans Tradex Enamels Semi Gloss is an oil based enamels designed for high traffic areas. Suitable for all interior timber and metal applications where a durable finish is desired. Resists dirt and stains, repels water and wipes clean easily. It is hard wearing and resists abrasion and hard knocks

USES

Suitable for all interior and sheltered exterior doors, trims and windows.

FEATURES AND BENEFITS

SCRUB RESISTANT	Provides a tough and durable abrasion-resistant coating
ADVANCED WASHABILITY	Resists burnishing – the formation of shiny patches on washing.
HIGH OPACITY	Excellent hiding properties.
EASY TO APPLY	Holds a wet edge longer to minimise lap marks and create a smooth uniform finish.
AUSTRALIAN MADE	Our Aussie Heritage: Since our inception over a century ago, we've been proudly manufacturing paint on our Aussie shores. We're proud to be an Australian manufacturing success, with plants in Villawood NSW, and Clayton VIC.
AUSTRALIAN STANDARD	AS2311, AS3730.5
ADVANCED FLOW MODIFIERS	Promotes ease of application, good flow properties and minimal roller splatter
ACRYLIC BINDER	Superior adhesion, flexibility, gloss retention & durability

PRODUCT SPECIFICATIONS

CLEAN UP	Mineral Turps
SEMI GLOSS	Offers good stain resistance and is easy to clean for high traffic areas that are subject to wear and tear.

DATASHEET

Ideal for all interior walls, bathrooms, laundries, doors and high traffic areas.

Ideal for exterior walls (recommended for weatherboards, roofs and trim), cement render / masonry, timber, galvanised iron, PVC piping and steel. Not suitable for surfaces used to collect drinking water

GLOSS LEVEL	40-50 (% at a 60 degree angle)
VOC LEVELS	388g/Litre
DRY TIMES: TOUCH DRY	4 hours
DRY TIMES: RECOAT	16 hours
4L AVAILABLE SIZES	4l
10L AVAILABLE SIZES	10l
SDS	SDS available from the Taubmans Website taubmans.com.au
WHITE BASE	Tint your desired colour from a White base

SURFACE PREPARATION

GENERAL INTERIOR	Can include interior walls, ceilings, doors and architraves
NEW WORK	<p>TIMBER Weathered (greyed) timber must be sanded to the original timber surface. Tannin rich timbers such as cedar may require two coats or use Taubmans Oil Based Wood Primer.</p> <p>GALVANISED IRON Thoroughly degrease new surfaces. Weathered surfaces should be thoroughly cleaned before painting. For structural galvanised iron, abrade with 240 grade paper to remove chemical treatments and allow full adhesion.</p> <p>CEMENT RENDER / MASONRY Allow masonry, cement render and mortar to cure for 28 days before painting.</p> <p>STEEL Remove rust and prime with a suitable Taubmans iron & steel primer or White Knight Rust Guard® Metal Primer.</p> <p>ZINCALUME® STEEL Wash with water and mild detergent. Surface must be clean and dry. Apply one coat of Taubmans 3 in 1 Prep.</p>
PREVIOUSLY PAINTED	Remove all loose and flaking paint. Apply Taubmans 3 in 1 Prep to aged enamel systems to provide intercoat adhesion.
AFTER PAINTING	Avoid exposure to steam for 48 hours. Surface may be washed after 7 days, but always avoid abrasive cleaners.
TEMPERATURE MIN	10 (°C)
TEMPERATURE MAX	35 (°C)
RECOATTEMPDEGREES	25 (°C)
RECOATHUMIDITYPERCENTAGE	50 (%)

DATASHEET

APPLICATION

WET FILM THICKNESS	60 - 65 microns
DRY FILM THICKNESS	25 - 30 microns
STIRRING	Stir paint with a wide flat stirrer in a circular lifting motion for at least 5 minutes before use. It is a requirement to stir paint before use to ensure that the colour tints are dispersed evenly throughout the paint. Continue stirring at regular intervals during application. Where more than one can of the same colour and product is required for a job, mix the contents of all the cans together to ensure colour consistency
BRUSH, ROLLER, SPRAY	Apply 1 or 2 coats (as per recommendation) by roller, brush or spray gun, with 2 hours between each coat. Paint the corners and edges with a narrow brush. Roll up to the edges using a quality synthetic or lambswool 10 - 12mm nap roller.
NAP ROLLER	7mm mohair roller cover or similar will give best results.
CURING	Avoid exposure to steam and condensation for 48 hours after painting.
COVERAGE	Up to 16m ² /litre. Coverage on rough or absorbent surfaces will be lower.
APPLICATION TEMPERATURE MINIMUM DEGREES CELCIUS	10
APPLICATION TEMPERATURE MAXIMUM DEGREES CELCIUS	35
COATS REQUIRED	Two

PRECAUTIONS

GENERAL SAFETY INFORMATION	<p>WALL PAINTS SAFETY</p> <p>Keep out of reach of children. Keep lid on when not in use. Avoid contact with skin and eyes: wear safety glasses and impervious gloves. Ensure area is well ventilated, wear a mask if spraying. Wash hands with soap and water after use.</p> <p>CEILING SAFETY</p> <p>Keep out of reach of children. Keep lid on when not in use. Do not thin for roller/brush application. Avoid contact with eyes: always wear safety glasses for eye protection when painting ceilings and do not paint directly overhead. Wear overalls and impervious gloves to avoid skin and clothing contact. Ensure area is well ventilated, wear a mask if spraying. Wash hands with soap and water after use.</p>
DANGER FLAMMABLE LIQUID AND VAPOUR	<p>Warning. Flammable hydrocarbon liquid. Keep out of reach of children. Keep lid on when not in use.</p> <p>Wear solvent resistant gloves and eye protection when using. Ensure adequate ventilation and do not breathe vapour.</p>
FIRST AID INFORMATION	<p>IF SWALLOWED - Do NOT induce vomiting. Seek medical advice immediately.</p> <p>EYE CONTACT - Flush with plenty of water. Always seek medical advice.</p> <p>SKIN CONTACT - Remove contaminated clothing and shoes. Wash skin thoroughly with soap and water.</p> <p>INHALATION - Remove to fresh air, seek medical advice if breathing is laboured.</p> <p>AUSTRALIA - 24 hour Medical Emergency Response Service: 1800 883 254 Taubmans Customer Service: 131 686 Further information: www.taubmans.com.au</p>
ENVIRONMENT INFORMATION	Do not pour leftover paint down the drain. Dispose of contents and container in accordance with all local, regional, national and international regulations. For responsible disposal of paint and packaging visit

ENVIRONMENT & SAFETY

WARRANTY INFORMATION

The Australian Paint Manufacturers' Federation has issued the following general warning to assist specifiers and end users understanding one of the key characteristics of oil based paint. All white and pale coloured enamels will yellow with age. These enamels will yellow more rapidly in areas of low natural light, when applied in poorly ventilated conditions, or in the presence of ammonia - common in water based paints and some household chemicals. Only the use of water based acrylics can assure resistance to yellowing.

DISCLAIMER

Any information provided by PPG Industries Australia Pty Ltd and its related entities relating to PPG products or their use and application (for example, information contained in a PPG paint system, Specification, or Data Sheet) is accurate and reliable at the time of publication. However, such information is general in nature. You must ensure that the information is current and suitable for the specific conditions for your project. If you need technical information for your circumstances, you should contact Taubmans Customer Service. PPG Industries Australia Pty Ltd and its related entities are not liable for any loss (including indirect, special or consequential loss, or loss of profits), expense, or damage suffered in connection with (a) such information, or (b) any information provided by a third party (including where that information is provided on a PPG website). Nothing in this disclaimer restricts, excludes or modifies or purports to restrict, exclude or modify any statutory rights under any applicable law including the Competition and Consumer Act 2010 (Cth) or the operation of any express guarantee.

CUSTOMER SERVICE/COMPANY CONTACT

Taubmans Customer Service: 131 686 Further information: www.taubmans.com.au