

DATASHEET

PPG

Trade Edge Under Coat



Product Code:
259500



Trade Edge Under Coat

Trade Edge Undercoat is a water based undercoat paint specifically developed to meet the needs of the trade painter. Trade Edge Interior Undercoat is a quick drying water based sealer with excellent filling and sanding properties.

USES

Undercoat for paper faced plasterboard and bare interior timber

FEATURES AND BENEFITS

ADVANCED WASHABILITY	Resists burnishing – the formation of shiny patches on washing.
EASY TO APPLY	Holds a wet edge longer to minimise lap marks and create a smooth uniform finish.
FLAT FINISH	Gives a flat finish with excellent surface defect hiding properties.
FAST DRYING	Assist project completion timelines with fast drying properties
AUSTRALIAN MADE	Our Aussie Heritage: Since our inception over a century ago, we've been proudly manufacturing paint on our Aussie shores. We're proud to be an Australian manufacturing success, with plants in Villawood NSW, and Clayton VIC.
TINTABLE	Tintable to over 10,000 colours. Order A4 samples or brush outs online at https://www.taubmans.com.au/specifiers/explore#search
AUSTRALIAN STANDARD	AS2311, AS3730.23
ADVANCED FLOW MODIFIERS	Promotes ease of application, good flow properties and minimal roller splatter
ACRYLIC BINDER	Superior adhesion, flexibility, gloss retention & durability
WATER BASED FORMULA	Easy clean up with water

PRODUCT SPECIFICATIONS

DATASHEET

LOW SHEEN	A subtle sheen level which is good for cleaning and hides surface imperfections better than gloss level paints. Ideal for all interior walls, all exterior walls, cement render / masonry, trim, roofs, timber, galvanised iron, PVC piping and steel
VOC LEVELS	31g/Litre
DRY TIMES: TOUCH DRY	30 mins
DRY TIMES: RECOAT	2 hours
15L AVAILABLE SIZES	15L
SDS	SDS available from the Taubmans Website taubmans.com.au
EXTENSIVE COLOUR RANGE	Tintable to over 10,000 colours. Order A4 samples or brush outs online at https://www.taubmans.com.au/specifiers/explore#search
WHITE BASE	Tint your desired colour from a White base

SURFACE PREPARATION

GENERAL INTERIOR	Can include interior walls, ceilings, doors and architraves
NEW WORK	<p>TIMBER Weathered (greyed) timber must be sanded to the original timber surface. Tannin rich timbers such as cedar should be primed with Taubmans 3 in 1 Prep or a suitable Taubmans oil based wood primer.</p> <p>GALVANISED IRON Thoroughly degrease new surfaces. Weathered surfaces should be thoroughly cleaned before painting. For structural galvanised iron, abrade with 240 grade paper to remove chemical treatments and allow full adhesion.</p> <p>CEMENT RENDER / MASONRY Allow masonry, cement render and mortar to cure for 28 days before painting.</p> <p>STEEL Remove rust and prime with a suitable Taubmans iron & steel primer or White Knight Rust Guard® Metal Primer.</p> <p>ZINCALUME® STEEL Wash with water and mild detergent. Surface must be clean and dry. Apply one coat of Taubmans 3 in 1 Prep.</p>
PREVIOUSLY PAINTED	Remove all loose and flaking paint. Apply Taubmans 3 in 1 Prep to aged enamel systems to provide intercoat adhesion.
AFTER PAINTING	Avoid exposure to steam for 48 hours. Surface may be washed after 7 days, but always avoid abrasive cleaners.
TEMPERATURE MIN	10 (°C)
TEMPERATURE MAX	35 (°C)
RECOATTEMPDEGREES	25 (°C)
RECOATHUMIDITYPERCENTAGE	50 (%)

APPLICATION

DATASHEET

WET FILM THICKNESS	60-65 microns
DRY FILM THICKNESS	25 - 30 microns
STIRRING	Stir paint with a wide flat stirrer in a circular lifting motion for at least 5 minutes before use. It is a requirement to stir paint before use to ensure that the colour tints are dispersed evenly throughout the paint. Continue stirring at regular intervals during application. Where more than one can of the same colour and product is required for a job, mix the contents of all the cans together to ensure colour consistency
BRUSH, ROLLER, SPRAY	Apply two coats by roller, brush or spray gun, with 2 hours between each coat. Paint the corners and edges with a narrow brush. Roll up to the edges using a quality synthetic or lambswool 10 - 12mm nap roller.
NAP ROLLER	10mm - 12mm Pile Roller
CURING	Avoid exposure to steam and condensation for 48 hours after painting.
COVERAGE	Up to 16m ² /litre.
MAINTENANCE - DECKING	No
APPLICATION TEMPERATURE MINIMUM DEGREES CELCIUS	10
APPLICATION TEMPERATURE MAXIMUM DEGREES CELCIUS	35
COATS REQUIRED	One

PRECAUTIONS

GENERAL SAFETY INFORMATION	Store in original container protected from direct sunlight in a dry, cool and well-ventilated area. Do not store below 5 deg C temperature. Keep containers sealed when not in use
FIRST AID INFORMATION	<p>IF SWALLOWED</p> <p>Do NOT induce vomiting. Seek medical advice immediately.</p> <p>EYE CONTACT</p> <p>Flush with plenty of water. Always seek medical advice.</p> <p>SKIN CONTACT</p> <p>Remove contaminated clothing and shoes. Wash skin thoroughly with soap and water.</p> <p>INHALATION</p> <p>Remove to fresh air, seek medical advice if breathing is laboured.</p> <p>AUSTRALIA</p> <p>24 hour Medical Emergency Response Service: 1800 883 254 Taubmans Customer Service: 131 686 Further information: www.taubmans.com.au</p>
ENVIRONMENT INFORMATION	Do not pour leftover paint down the drain. Dispose of contents and container in accordance with all local, regional, national and international regulations. For responsible disposal of paint and packaging visit paintback.com.au

DISCLAIMER

Any information provided by PPG Industries Australia Pty Ltd and its related entities relating to PPG products or their use and application (for example, information contained in a PPG paint system, Specification, or Data Sheet) is accurate and reliable at the time of publication. However, such information is general in nature. You must ensure that the information is current and suitable for the specific conditions for your project. If you need technical information for your circumstances, you should contact Taubmans Customer Service. PPG Industries Australia Pty Ltd and its related entities are not liable for any loss (including indirect, special or consequential loss, or loss of profits), expense, or damage suffered in connection with (a) such information, or (b) any information provided by a third party (including where that information is provided

DATASHEET

on a PPG website). Nothing in this disclaimer restricts, excludes or modifies or purports to restrict, exclude or modify any statutory rights under any applicable law including the Competition and Consumer Act 2010 (Cth) or the operation of any express guarantee.

CUSTOMER SERVICE/COMPANY CONTACT

Taubmans Customer Service: 131 686 Further information: www.taubmans.com.au